AMENDMENTS TO THE CLAIMS

Please amend the claims as follows:

(Currently Amended) A coated material for paper material comprising a hydroxyl group, having a surface to which a silane-based coating solution is applied and hardened/solidified by the action of a catalyst.

wherein said coating solution is a solvent solution comprising comprises:

(a) a compound represented by formula 1

$$R_{1}O \begin{bmatrix} R_{4} \\ S_{1} \\ O \\ OR_{2} \end{bmatrix}_{n}$$
 (1)

wherein R_1 , R_2 , R_3 and R_4 are independently a hydrogen or an alkyl group having 1-4 carbons and n=2-10;

(b) a compound represented by formula 3 having two hydrolyzable substituents and two unhydrolyzable substituents

wherein R_9 and R_{11} are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_{10} and R_{12} each is independently selected from the group consisting of an alkyl group having 1-10 carbon atoms, an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 3 wherein at least one of R_9 0 and R_{11} 0 represent a siloxane bond,

wherein the compound of formula 3 is added to the coating solution in an amount not exceeding 50% of the amount of formula 1 present in said coating solution;

(c) a hydrolysable organometallic compound;

wherein the surface is formed where said hydrolyzable organometallic compound is used as a catalyst for hardening/solidifying said coating solution; and

wherein the surface is formed where one or more organometallic compounds selected from the group consisting of titanium, zirconium, aluminum and tin is/are used as said hydrolyzable organometallic compound; and

(d) a solvent;

wherein the compound represented by formula 1, the compound represented by formula 3 and the hydrolysable organometallic compound are dissolved in said solvent.

2. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 1, wherein the surface is formed where, prior to the application of the coating solution, said fiber material is dipped in alcohol and dried and ultraviolet ray is further irradiated thereto.

3. - 4. (Canceled)

5. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 1, wherein the surface is formed where, in addition to formula 1, a coating solution containing a compound represented by formula 2 having three hydrolyzable substituents and one unhydrolyzable substituent is used as the coating solution of a silane type

wherein R_5 , R_6 and R_7 are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_8 is selected from the group consisting of an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl groups having an epoxy group or a glycidyl group; or a condensate of said formula 2 wherein at least one of R_5O , R_6O and R_7O represent a siloxane bond, and

wherein the compound of formula 2 is added to the coating solution in an amount not exceeding 50% of the amount of formula 1 present in said coating solution.

6. (Canceled)

7. (Currently Amended) A coated material for paper material comprising a hydroxyl group, having a surface to which a silane-based coating solution is applied and hardened/solidified by the action of a catalyst,

wherein said coating solution is a solvent solution comprising comprises:

(a) a compound represented by formula 1

$$R_1O \begin{bmatrix} R_4 \\ S_1 \\ OR_2 \end{bmatrix}_n R_3 \qquad (1)$$

wherein R_1 , R_2 , R_3 and R_4 are independently a hydrogen or an alkyl group having 1-4 carbons and n=2-10;

(b) a compound represented by formula 2

$$R_8$$
 R_6O
 Si
 OR_7
 OR_6
 OR_6
 OR_6
 OR_6
 OR_6
 OR_6
 OR_6
 OR_6

(c) a compound represented by formula 3

$$R_{9}O \longrightarrow Si \longrightarrow OR_{11}$$
 (3)

wherein in formulae (2) and (3) R_5 , R_6 and R_7 are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_8 is selected from the group consisting of an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 2 wherein at least one of R_5O , R_6O and R_7O represent a siloxane bond: and

wherein R_9 and R_{11} are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_{10} and R_{12} each is independently selected from the group consisting of an alkyl group having 1-10 carbon atoms, an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 3 wherein at least one of R_9O and $R_{11}O$ represent a siloxane bond,

wherein the compounds of formula 2 and formula 3 are added to the coating solution in an amount such that the total amount of formula 2 and formula 3 does not exceed 50% of the amount of formula 1 present in said coating solution;

(d) a hydrolysable organometallic compound;

wherein the surface is formed where said hydrolyzable organometallic compound is used as a catalyst for hardening/solidifying said coating solution; and

wherein the surface is formed where one or more organometallic compounds selected from the group consisting of titanium, zirconium, aluminum and tin is/are used as said hydrolyzable organometallic compound; and

(e) a solvent:

wherein the compound represented by formula 1, the compound represented by formula 2, the compound represented by formula 3, and the hydrolysable organometallic compound are dissolved in said solvent.

- 8. (Currently Amended) A coating solution of a silane type for giving an appropriate strength and good light transmitting and water repelling properties to a fiber material where said coating solution is a solvent solution comprising comprises
 - (a) a compound represented by formula 1

$$R_1O \begin{bmatrix} R_4 \\ S_1 \\ OR_2 \end{bmatrix}_n$$
 (1)

wherein R_1 , R_2 , R_3 and R_4 are independently a hydrogen or an alkyl group having 1-4 carbons and n=2-10;

(b) a compound represented by formula 3 having two hydrolyzable substituents and two unhydrolyzable substituents

$$R_{12}$$
 $R_{9}O \longrightarrow Si \longrightarrow OR_{11}$ (3)

wherein R_9 and R_{11} are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_{10} and R_{12} each is independently selected from the group consisting of an alkyl group having 1-10 carbon atoms, an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said-formula 3 wherein at least one of R_9O and $R_{11}O$ represent a siloxane bond.

wherein the compound of formula 3 is added to the coating solution in an amount not exceeding 50% of the amount of formula 1 present in said coating solution;

(c) a catalyst for hardening/solidifying thereof,

wherein the catalyst for hardening/solidifying the coating solution of a silane type is one or more organometallic compounds selected from the group consisting of titanium, zirconium, aluminum and tin; and

(d) a solvent;

wherein the compound represented by formula 1, the compound represented by formula 3, and the catalyst are dissolved in said solvent.

9. - 10. (Canceled)

11. (Previously Presented) The coating solution of claim 8, wherein the coating solution of a silane type contains a compound represented by formula 2 having three hydrolyzable substituents and one unhydrolyzable substituent in addition to the compound of formula 1

$$R_8$$
 R_50
 R_50
 R_7
 R_8
 R_7
 R_7
 R_8
 R_7
 R_8
 $R_$

wherein R_5 , R_6 and R_7 are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms and an alkenyl group having 1-10 carbon atoms; and R_8 is an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 2 wherein at least one of R_5O , R_5O and R_7O represent a siloxane bond, and

wherein the compound of formula 2 is added to the coating solution in an amount not exceeding 50% of the amount of formula 1 present in said coating solution.

12. (Canceled)

- 13. (Currently Amended) A coating solution of a silane type for giving an appropriate strength and good light transmitting and water repelling properties to a fiber material, wherein the coating solution of a silane type is a solvent solution comprising eemprises
 - (a) a compound represented by formula 1

$$R_{1}O \begin{bmatrix} R_{4} \\ S_{1} \\ OR_{2} \end{bmatrix}_{n} R_{3} \qquad (1)$$

wherein R_1 , R_2 , R_3 and R_4 are independently a hydrogen or an alkyl group having 1-4 carbons and n=2-10;

(b) a compound represented by formula (2)

(c) a compound represented by formula 3

$$R_{9}O \longrightarrow Si \longrightarrow OR_{11}$$
 (3)

wherein in formulae (2) and (3) R_5 , R_6 and R_7 are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms, and an alkenyl group having 1-10 carbon atoms; and R_8 is selected from the group consisting of an alkenyl group having 1-10 carbon atoms, Θ a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 2 wherein at least one of R_5O , R_6O and R_7O represent a siloxane bond; and

wherein R_9 and R_{11} are independently selected from the group consisting of a hydrogen, an alkyl group having 1-10 carbon atoms, and an alkenyl group having 1-10 carbon atoms; and R_{10} and R_{12} each is independently selected from the group consisting of an alkyl group having 1-10 carbon atoms, an alkenyl group having 1-10 carbon atoms, a phenyl group, and a phenyl group having an epoxy group or a glycidyl group; or a condensate of said formula 3 wherein at least one of R_9O and $R_{11}O$ represent a siloxane bond, and

wherein the compounds of formula 2 and formula 3 are added to the coating solution in an amount such that the total amount of formula 2 and formula 3 does not exceed 50% of the amount of formula 1 present in said coating solution,

(d) a catalyst for hardening/solidifying thereof,

wherein the catalyst for hardening/solidifying the coating solution of a silane type is one or more organometallic compounds selected from the group consisting of titanium, zirconium, aluminum and tin; and

(e) a solvent;

wherein the compound represented by formula 1, the compound represented by formula 2, the compound represented by formula 3, and the catalyst are dissolved in said solvent.

- 14. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 7, wherein the surface is formed where, prior to the application of the coating solution, said fiber material is dipped in alcohol and dried and ultraviolet ray is further irradiated thereto.
- 15. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 1, wherein when any of $R_9 R_{12}$ is an alkyl group having 1 to 10 carbon atoms.
- 16. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 1, wherein when any of $R_9 R_{12}$ is an alkenyl group having 1 to 10 carbon atoms.
- 17. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 7, wherein when any of $R_9 R_{12}$ is an alkyl group having 1 to 10 carbon atoms.
- 18. (Currently Amended) The coated <u>paper material or fiber</u> material according to claim 7, wherein when any of $R_9 R_{12}$ is an alkenyl group having 1 to 10 carbon atoms.

Application Serial No. 09/874,055 Reply to Office Action of May 4, 2007

- 19. (Previously Presented) The coating solution according to claim 8, wherein when any of $R_9 R_{12}$ is an alkyl group having 1 to 10 carbon atoms.
- 20. (Previously Presented) The coating solution according to claim 8, wherein when any of R_9-R_{12} is an alkenyl group having 1 to 10 carbon atoms.
- 21. (Previously Presented) The coating solution according to claim 13, wherein when any of $R_9 R_{12}$ is an alkyl group having 1 to 10 carbon atoms.
- 22. (Previously Presented) The coating solution according to claim 13, wherein when any of $R_9 R_{12}$ is an alkenyl group having 1 to 10 carbon atoms.

SUPPORT FOR THE AMENDMENTS

Claims 3, 4, 6, 9, 10, and 12 were previously canceled.

Claims 1, 2, 5, 7, 8, and 13-18 have been amended.

Support for the amendment of Claims 1, 7, 8, and 13 is provided by the corresponding previously pending claims, the specification as filed, for example at page 15, line 21 to page 17, line 3, page 20, lines 7-12 and page 21, lines 12-20, and the Examples. The amendment of Claims 1, 2, 5, 6, and 14-18 find additional support on page 1, lines 5-11.

No new matter has been entered by the present amendment.